

Bakelite Paper Tube TEST REPORT

item	unit	index	
		ID=5~25mm	ID≥25mm
Density	—	1.03	1.1
Flexural Strength ≥	MPa	49	58.8
Compressive Strength≥	MPa	49	58.8
Thermal stability	°C	120	120
Water Absorption	%	—	3~10
medium wastage FACTOR (50Hz) ≤	—	0.03	0.03
Resistance Voltage Perpendicular to Laminations(90 ±2°C OIL,5min) Thickness 1.5~2.5mm thickness >2.5~3.5mm thickness >3.5~4.5mm thickness 4.5~6.0mm thickness >6.0mm	kV/mm	8.5 8.0 7.0 6.5 6.0	8.5 8.0 7.0 6.5 6.0
Resistance Voltage Perpendicular to Laminations(90 ±2°C OIL,5min) ≥	kV	20	25
Surface Resistance Voltage	kV	12	12
length	mm	1000±50,1500±50,2000±50	



TEL:+86-512-67081529 FAX:+86-512-65256838

E.mail:sale@wellele.com,info@wellele.com

http://www.wellele.com,allinsulating.com,fusestube.com

Addsuli RD47,Caizhi 5-712,suzhou,jiangsu
