

Vulcanized fiber and Epoxy Fiberglass Roll Combination Tube

category	parameter			
Temperature resistance	100°C			
Product appearance color	Varnish, gray UV paint, other colors can be customized			
Inner diameter range	6~20mm (Can be customized)			
Surface finish	Can be processed according to customer needs			
mechanical strength	high			
Performance test data				
Serial number	Test item	Company	Requirement	
1	density	g/cm ³	≥1.70	
2	Water absorption	%	≤6	
3	Shear strength	Mpa	≥80	
4	Bending strength	Mpa	≥160	
5	compressive strength	Mpa	≥90	
6	Vertical resistance voltage (Normal 5min)	KV	42	
	wall thickness	2.0	KV	14
	Cm	2.5	KV	16



TEL:+86-512-67081529 FAX:+86-512-65256838
E.mail:sale@wellele.com,info@wellele.com
http://www.wellele.com ,allinsulating.com,fusestube.com
Add:suli RD47.Caizhi 5-712, SUZHOU, JIANGSU

	3.0	KV	18
	4.0	KV	20
	5.0	KV	24
	6.0	KV	28
	7.0	KV	30
	8.0	KV	34

Note: the above test data for the sample test data, our company can customize products according to customer needs.